

Template

Oboe Nr. 006



Values of the scraping-thickness
in hundredths of millimetres

middle	0.7 mm	1.4 mm	2.1 mm	2.8 mm	3.5 mm	edge
8	8	7	7	6	6	tip
11	11	10	9	8	7	0.7 mm
20	19	17	14	11	9	1.4 mm
30	29	25	21	17	11	2.1 mm
35	34	29	25	20	14	2.8 mm
38	37	32	28	23	17	3.5 mm
40	39	35	31	26	20	4.2 mm
42	41	37	33	28	22	4.9 mm
43	42	38	34	30	24	5.6 mm
44	43	39	36	32	26	6.3 mm
45	44	40	38	34	28	7.0 mm
46	45	41	39	35	30	7.7 mm
46	45	42	40	37	32	8.4 mm
47	46	43	41	38	33	9.1 mm
47	46	43	41	39	34	9.8 mm
48	47	44	42	40	35	10.5 mm
48	47	44	42	40	36	11.2 mm
49	48	45	43	41	37	11.9 mm



Oboenzubehör Bucher GmbH

Bösch 41
CH-6331 Hünenberg

tel. + 41 (0)41 780 40 58
e-mail bucher@oboerohr.ch
website www.oboerohr.ch